



CLEAR ULTRA SHEEN 7000 AC 1315 - AIM

ASTM C-1315 TYPE 1, CLASS A ACRYLIC CONCRETE

CURING AND SEALING COMPOUND • NON-YELLOWING • SLIP RESISTANT • GLOSS

VOC Content: 341 gr./liter or 2.84 #/gal. – Cure

DESCRIPTION

CLEAR ULTRA SHEEN 7000 AC1315 AIM continues Vexcon Chemical's leadership in the development of break through polymer technology. CLEAR ULTRA SHEEN 7000 AC1315 AIM is the highest solids cure and seal on the market today offering superior gloss, greater long term protection, fast drying and easier application. CLEAR ULTRA SHEEN 7000 AC1315 AIM quickly forms a hard clear film that is permanent, tough, chemical and slip resistant, water repellent, dustproof, and non-yellowing. CLEAR ULTRA SHEEN 7000 AC1315 AIM features Vexcon's breathable technology which allows moisture vapor to pass through rather than becoming trapped, preventing whitening, peeling and flaking. The product is ideal for both interior and exterior applications on new and existing floors, stamped and decorated concrete surfaces. It contains no fillers, modifiers or extenders that can cause sealers to yellow. Independent laboratory testing confirms that the product's non-yellowing characteristics outlast and out perform competitive products.

BENEFITS

- Non-Yellowing
- Superior film gloss
- Fast track installation
- Greater long-term wear resistance
- Provides for complete development of concrete's wear resistance and strength properties
- Apply to damp surfaces without whitening or loss of adhesion
- Seals and hardens surface reducing clean up and maintenance
- Can be applied to 20° F
- Excellent protection against staining, attack by alkali, oil, salt, cleaners and common industrial chemicals
- Prevents efflorescence, dusting and spalling
- Vexcon breathable technology
- Re-coatable

APPLICATION

- Product is supplied at the proper consistency for application and dilution will reduce efficiency and gloss.
- Thoroughly mix before applying.
- To improve non-slip profile use **Certi-Vex® Grip**.
- Note; product forms a surface film quickly depending on temperature, humidity and wind conditions therefore, for best results follow all equipment and application instructions carefully.
- Review Application Tips for High Solid Sealers, Vexcon TN192 for more detailed application information.

If applying by sprayer:

- Apply by low-pressure high solids commercial grade solvent resistant sprayer with neoprene fittings. (Do not use garden or form oil sprayers).
- The sprayer must be clean and dry. If cleaning with solvents is required, use **Certi-Vex® Equipment Cleaner**.

Clean sprayer as directed between applications to ensure best results.

- If spraying and back rolling, best application is to spray enough material that a second person can immediately back roll following the spray applicator. Follow roller instructions below. Caution; do not delay the back roll as the area will dry quickly.

If applying by roller:

- For best results use Vexcon's **EvenFlow Applicator** or ¼ " nap mohair roller.
- Do not over-work material, apply in a single lapping motion. Do not roll area back and forth, this can cause the film to break and product to become stringy.
- Do not run roller dry, keep a wet edge and do sections small enough to roll only once over wet material.
- Do not roll over dry material this can cause the product to become stringy. To aid in keeping roller wet and fluid, keep a roller pan filled with **Certi-Vex® Equipment Cleaner**.
- Over rolling or using incorrect rollers will cause bubbles to form in the coating. If this occurs on final coat corrective procedure is to apply a light coat of **Certi-Vex Equipment Cleaner** over the area. This will recast (heel) the coating and eliminate the bubbles. If this occurs on first coat, follow corrective procedure above then apply final coat.
- Material should not be allowed to puddle.
- Do not allow sealed area to become wet with water until dry. See dry times.
- Protect all surrounding areas from over spray.
- The sealer can be applied to damp surfaces, however, do not apply over puddled water.
- A uniform appearance requires even coats leaving no gaps. Some areas may be more porous than others; these areas may require additional coats to even out the appearance. Caution: Do not over-apply material. See special notes section.

CURING AND SEALING NEW CONCRETE

- Apply **Certi-Vex AC1315 AIM** to still damp freshly finished concrete as soon as the surface cannot be marred, and water sheen disappears. Do not apply over freestanding water.
- If application is delayed, concrete must be kept wet (preferably by water spray mist) until product can be applied.
- If concrete is allowed to dry use **Certi-Vex® Concrete Etch & Efflorescence Remover** to clean and prepare the surface.
- Apply first coat at 300-400 sq.ft/gal (7.5 m²/L). A second coat is recommended for long term durability. See Second Coat section.

SURFACE PREPARATION EXISTING CONCRETE

The concrete surface must be properly repaired, structurally sound and cleaned. Use Vexcon's surface prep and cleaning products to properly clean the surface prior to application.

- To remove coatings such as epoxy's, sealers and curing compounds use **Certi-Vex® Concrete Stripper**.
- The concrete should be cleaned with **Certi-Vex® Super Degreaser & Cleaner** to remove any dust, dirt or debris and allowed to dry for a minimum of 24 hours after cleaning.
- To remove efflorescence or to etch the surface for improved material penetration use **Certi-Vex® Etch & Efflorescence Remover**.
- There should be no freestanding water.
- Large cracks should be repaired using **PowerCoat® Epoxy Joint Sealant**.

SEALING EXISTING CONCRETE

- Prior to application a test area must be performed to determine proper application rate and required surface preparation.
- To determine that the concrete is penetrable perform a water absorbency test by applying water to a representative portion of the prepared concrete floor. A properly prepared surface when dry will immediately absorb clean water without any surface beading effects.
- If required use **Certi-Vex® Etch & Efflorescence Remover** to improve sealer penetration. Application to still damp surfaces is acceptable however free standing water must be removed.
- Apply **CLEAR ULTRA SHEEN 7000 AC 1315 AIM** at 400-500 sq.ft. /gal (10-12.5 m²/L) on hard non-porous floors and 250-300 sq.ft. /gal (6.2-7.5 m²/L) on porous floors.

SECOND COAT

Apply after 1st coat has dried at 500-600 sq.ft. /gal (12.5-15 m²/L).

SPECIFICATIONS/COMPLIANCE

- VOC: 341 gr./liter or 2.84 #/gal. – Cure
- Meets USEPA AIM and OTC VOC regulations
- ASTM C 1315 Type 1, Class A
- AASHTO M-148
- ASTM C 309, Type 1, Class A&B.
- Federal specification TT-C-800-A (GSA-FSS) type 1
- USDA approved
- ASTM G154 – passes Class A 300 hour UV resistance
- Meets ADA and ASTM D 2047 non-slip

TOPCOATS AND ADHESIVES

CLEAR ULTRA SHEEN 7000 AC1315 AIM cured concrete can be topcoated with a variety of paints, adhesives and mastics a minimum of 28 days after application. It is strongly suggested that a test area be applied prior to coating the entire surface, since products can adhere to concrete in varying degrees. Check with manufacturer of the topcoat for any precautionary and compatibility information.

MAINTENANCE

Spills should be removed promptly and cleaned. Sealed areas should be cleaned regularly, use **Certi-Vex® Super Degreaser & Cleaner** for all cleaning requirements. Periodic reapplication may be required as the sealer wears off.

SPECIAL NOTES

- To assist in application note, 200 sq.ft. /gallon is equal to the thickness of a sheet of paper
- Will tend to show rubber burns or tire marks
- Will cause bleeding of bituminous surfaces
- May enhance mottling of colored surfaces
- Not gasoline resistant, use **Powercoat® Epoxy** products
- Application of more than two coats is not recommended
- Over application may lead to surface discoloration and improper sealer performance
- Do not apply more material per square foot than specified.
- Can apply when surface temperatures are 20° F - 85° F, when below or above these ranges review Vexcon's Cold and Hot Weather Application Guides
- Shelf Life: If properly stored in its original sealed container, three years from date of manufacture. Rotate your stock
- For use by experienced applicators

PACKAGING

CLEAR ULTRA SHEEN 7000 AC1315 AIM is available in 55-gallon drums and 5-gallon pails. Contact Vexcon to discuss your customized packaging requirements.

VITAL STATISTICS

- | | |
|----------------------------|--------------------------------|
| • Flash Point (TCC) | 1.4° F |
| • Boiling Point (706 mmHg) | 133° F (56°C) |
| • Autoignition Temp | ND |
| • Extinguishing Media | Foam, dry chemical, CO2, Water |

PHYSICAL PROPERTIES

- | | | | |
|------------------|---------------|-------------------|---------------|
| • Wet appearance | Water white | • Dry appearance | Clear |
| • Dry to touch | 20-25 minutes | • Dry - tack free | 30-45 minutes |
| • Foot traffic | 1 hour | • Vehicle traffic | Overnight |
| • Solids | 35% minimum | | |

Note: All calculations based upon 68-77° F (20-25° c).

Lower temperatures and relative humidity will extend dry times.

HEALTH AND SAFETY

CAUTION FLAMMABLE LIQUID

- Resin solution, flammable liquid, red label
- Use of respirators is mandatory when using this product in confined areas.
- Use only with adequate ventilation.
- If swallowed, do not induce vomiting.
- Use of gloves, goggles and other protective clothing is advised when using this product.

STAMPCRETE MSDS #CS114 is an integral part of the safety and application of our product. A short synopsis is provided in this product data sheet, CS114. Before using this Stampcrete product obtain a copy of the MSDS from your distributor or by contacting Stampcrete.

CONTACT US @

Additional product information, technical assistance and customer service is available by contacting Stampcrete directly or our distributors.

- Voice: 800-233-3298
- Fax: 315-451-7644